

SPECIFICATION SHEET

Commodity	: Polyester Cationic Dyeable Chips
Application	: Textile, Yarns, Filament
Origin	: Thailand

Specification	Unit	Spec
IV (Phenol:DCB 60:40 w/w at 25 C, 0.5%conc)	dl/g	0.545 ± 0.015
Free Acid (-COOH)	meq/kg	≤ 48.0
DEG (GC-Methanolysis)	%	3.25 ± 0.30
Melting Point (DSC)	°C	242.0 ± 2.0
Colour values		
CIE L* a* b* Amorphous Chips.		
L*		Min. 65.0
b*		Max. 2.80
Chips/gm (Balance)	Nos.	40 ± 5
Ash (w/w) 850 C	%	-

Remarks: TiO₂ content 0.30 wt% , Salt content:1.6% mole.

QAC-S-01/01

Packing	: 1000KGS IN PP WOVEN JUMBO BAGS
Container Loading	: 20MT (20BAGS) IN 1 X 20FT CONTAINER



Copyright Tesport 2020

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Tesport F.T. cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Adnan Kahveci Mah.
Sayaca Cad. Ekol Center
Kat 2 No:50 Beylikduzu
Istanbul - Turkey
Tel: +90 212 856 05 01
www.tesport.com
resin@tesport.com