

01 January 2019

SALES SPECIFICATIONS

ETHYLENE GLYCOL POLYESTER GRADE SPECIFIED MATERIAL: 000101232907

TEST ITEM	METHOD	ETHYLENE GLYCOL POLYESTER GRADE
Purity, %wt, minimum	BY DIFFERENCE	99.9
Diethylene Glycol, %wt, maximum	ASTM E2409	0.05
Acidity, ppm, maximum, as Acetic Acid	ASTM E2679	20
Iron, ppm, maximum	ASTM E1615	0.1
Chlorides, ppm, maximum	ASTM E2469	0.2
UV Transmit @ 220nm, %T, minimum	ASTM E2193	70
UV Transmit @ 250nm, %T, minimum	ASTM E2193	90
UV Transmit @ 275nm, %T, minimum	ASTM E2193	94
UV Transmit @ 350nm, %T, minimum	ASTM E2193	98
Water, %wt, maximum	ASTM E1064	0.05
Color, Platinum-Cobalt Units, maximum	ASTM D5386	5
Appearance	ASTM E2680	Pass

Typical values for Specific Gravity (20/20°C): 1.1151 – 1.1156

Typical values for Refractive Index at 20°C: 1.4305 – 1.4330

Typical values for Ash content: < 10ppm

Typical values for Distillation Range: 196°C – 200°C



Copyright Tesport 2020

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Tesport F.T. cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Adnan Kahveci Mah.
Sayaca Cad. Ekol Center
Kat 2 No:50 Beylikduzu
Istanbul - Turkey
Tel: +90 212 856 05 01
www.tesport.com
resin@tesport.com